

# The influence of Fe-oxides and organic matter on surface properties of nanostructured microaggregates of the Terra rossa and Calcocambisol

---

**Ružičić, Stanko; Durn, Goran; Sondi, Ivan; Cukrov, Nuša; Škapin, Srečo D.; Vdović, Neda**

*Source / Izvornik:* **Conference book / 9th Mid-European Clay Conference, 2018**

**Conference paper / Rad u zborniku**

*Permanent link / Trajna poveznica:* <https://urn.nsk.hr/urn:nbn:hr:169:597399>

*Rights / Prava:* [In copyright](#)/[Zaštićeno autorskim pravom.](#)

*Download date / Datum preuzimanja:* **2024-12-04**



*Repository / Repozitorij:*

[Faculty of Mining, Geology and Petroleum Engineering Repository, University of Zagreb](#)



# The influence of Fe-oxides and organic matter on surface properties of nanostructured microaggregates of the Terra rossa and Calcocambisol

**Stanko Ružičić<sup>1</sup>, Goran Durn<sup>1</sup>, Ivan Sondi<sup>1</sup>, Nuša Cukrov<sup>2</sup>, Srečo D. Škapin<sup>3</sup> and Neda Vdović<sup>2</sup>**

<sup>1</sup>University of Zagreb, Faculty of Mining, Geology and Petroleum Engineering, 10000 Zagreb, Croatia  
(stanko.ruzicic@rgn.hr)

<sup>2</sup>Ruder Bošković Institute, Center for Marine and Environmental Research, 10000 Zagreb, Croatia

<sup>3</sup>Jožef Štefan Institute, Advanced Materials Department, 1000 Ljubljana, Slovenia

This study investigates the influence of Fe-oxides and organic matter on surface properties of nanostructured mineral microaggregates obtained from the Terra rossa and Calcocambisol developed on hard limestone and dolomite in Istria, Croatia.

The mineral composition and the morphology of samples (B horizon) were investigated using X-ray diffraction and field emission scanning electron microscope (FE-SEM), respectively. In order to determine the influence of Fe-oxides and organic matter coatings on surface properties of soils, samples were selectively dissolved. Particle size distribution, specific surface area (SSA), and electrophoretic mobility (EPM) were measured on the following soil subsamples: original samples, samples treated with H<sub>2</sub>O<sub>2</sub>, samples treated with H<sub>2</sub>O<sub>2</sub>+NH<sub>4</sub>-oxalate, and samples treated with H<sub>2</sub>O<sub>2</sub>+NH<sub>4</sub>-oxalate+Na-dithionite-citrate-bicarbonate. The obtained results showed that kaolinites (kaolinites which form intercalation compounds with DMSO-KI<sub>D</sub> and kaolinites which do not intercalate with DMSO-KI) (RANGE et al., 1969), illitic material (ŠRODOŃ, 1984; ŠRODOŃ & EBERL, 1984), and Fe-oxides are the main mineral components in the clay fraction of the terra rossa. Calcocambisol enriched in organic matter contains kaolinites, chlorite and vermiculite as main mineral phases. The main differences in surface properties between the Terra rossa and Calcocambisol were a consequence of diverse particle-size distribution, mineral composition, and the share of organic matter. FE-SEM analysis of the Terra rossa and Calcocambisol samples after removal of amorphous Fe-oxides and organic matter shows disintegration. This disintegration is evident in reducing particle size from 2 µm to 50 nm for the Terra rossa and from 1.8 µm to 50 nm for Calcocambisol, respectively. Kaolinite with particle size about 50 nm shows pseudo-hexagonal form in analysed soils. The SSA increased proportionally to the amount of the removed organic matter in both soils. After the removal of well-crystallized Fe-oxides the SSA slightly decreased in Calcocambisol and significantly increased in the Terra rossa due to major soil microaggregate decomposition. EPM measurements of investigated samples were diverse.

## Acknowledgments

This study was financed by Croatian Science Foundation (grant 2504).

## References:

- ŠRODOŃ, J. (1984): X-ray powder diffraction identification of illitic materials.- *Clays and Clay Minerals*, 32, 337-349.
- ŠRODOŃ, J. & EBERL, D.D. (1984): Illite.- In: BAILEY, S.W. (ed.): *Micas. Reviews in Mineralogy*, 13, Mineralogical Society of America, 495-544.
- RANGE, K.J., RANGE, A. & WEISS, A. (1969): Fire-clay type kaolinite or fire-clay mineral? Experimental classification of kaolinite-halloysite minerals.- *Proceedings of the 3<sup>rd</sup> International Clay Conference, Tokyo 1*, 3-13.